



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : D01F 9/04, 2/28, A61L 15/28	A1	(11) International Publication Number: WO 97/39170 (43) International Publication Date: 23 October 1997 (23.10.97)
(21) International Application Number: PCT/EP97/01880 (22) International Filing Date: 11 April 1997 (11.04.97) (30) Priority Data: 9607600.5 12 April 1996 (12.04.96) GB 9618658.0 6 September 1996 (06.09.96) GB (71) Applicant (for all designated States except US): BRISTOL-MYERS SQUIBB COMPANY [US/US]; 345 Park Avenue, New York, NY 10154 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): KERSHAW, David [GB/GB]; The Flat, Greyhound Vaults, Market Street, Abergavenny, Gwent NP7 5SD (GB). MAHONEY, Peter, M., J. [GB/GB]; Lletty Meirch Farm, Llanfihangel-Ng-Nhwyntfa, Near Llanfyllin, Powys SY22 5JF (GB). HANMER, Paul [GB/GB]; Brackenwood, Alltami Road, Buckley, Flintshire CH7 3PD (GB). PRITCHARD, David [GB/GB]; 18 Parc-Y-Fro, Creigau, Cardiff, South Glamorgan CF4 8SA (GB). (74) Agent: MAYS, Julie; Bristol-Myers Company Limited, Patent Dept., Swakeleys House, Milton Road, Ickenham, Uxbridge UB10 8NS (GB).		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: COMPOSITE FIBRES, WOUND DRESSINGS INCORPORATING SUCH FIBRES AND A METHOD FOR MAKING SAME		
(57) Abstract An absorbent, composite fibre comprising a matrix of from 10 % to less than 50 % of water insoluble alginate having dispersed therein at least 40 % of another polysaccharide.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

5 COMPOSITE FIBRES, WOUND DRESSINGS INCORPORATING SUCH
 FIBRES AND A METHOD FOR MAKING SAME

 The invention relates to composite fibres, particularly
absorbent composite fibres for use in wound treatment,
10 wound dressings incorporating such fibres and a method for
making same.

 Absorbent fibres for use in wound treatment are well known
in the art. Examples include cellulose fibres, chemically
15 modified cellulose fibres, pectin fibres, alginate fibres,
chitosan fibres, hyaluronic acid fibres or other
polysaccharide fibres or fibres derived from gums. In the
treatment of wounds it is desirable to use fibres made from
pectin or carboxymethyl cellulose but the known processes
20 for making such fibres are complex and expensive and the
resulting fibres not always viable. For instance it is
known to make carboxymethyl cellulose fibres by chemically
converting preformed cellulose fibres. It is also known
that both pectin fibres and carboxymethyl cellulose fibres
25 are difficult to spin.

 It has been proposed in GB 2062652 A to make cellulose
fibres comprising anionically modified polysaccharides by
adding the polysaccharide to preformed viscose. Similarly
30 in US 4063558 there is described a method for making fibres
of cellulose with alkali metal salts of alginic acid
uniformly dispersed therein by adding a solution of sodium
alginate to preformed viscose.

- 5 In WO 96/10106 there are described fibres which preferably comprise from 70 to 95% by weight of an alginate co-spun with from 5 to 30% by weight of at least one water soluble organic polymeric species (other than alginate).
- 10 We have now found that it is possible to make a composite, absorbent fibre comprising a matrix of water insoluble alginate having another polysaccharide dispersed therein where the fibre comprises less than 50% by weight of the alginate, the fibre mitigating the disadvantages of the
- 15 prior art fibres.

Accordingly the invention provides an absorbent, composite fibre comprising a matrix of at least 10% and less than 50% by weight of water insoluble alginate having dispersed

20 therein at least 40% of another polysaccharide. Unless otherwise stated all percentages herein are by weight based on the weight of the fibre.

Whilst not wishing to be bound by theory it is believed

25 that the water insoluble alginate effectively provides, as a matrix, a molecular backbone to the fibre that enables the other polysaccharides to be incorporated and results in a fibre that may be spun and otherwise processed. The use of water insoluble alginate for this purpose enables the

30 fibres to be made without the need for complex and expensive processing and without the need to use preformed cellulose as a starting material. Preferred polysaccharides for addition to the alginate backbone are carboxymethyl cellulose and/or pectin.

5 Since it is believed that the fibres of the invention rely on the water insoluble alginate to provide integrity to the fibres it is truly surprising that it is possible to make viable fibres processable into products that comprise a minor proportion of insoluble alginate. One of the
10 advantages of such fibres is that they may comprise a major proportion of polysaccharide other than alginate which generally makes them more absorbent than fibres which have insoluble alginates in a major proportion.

15 Preferably the fibres comprise, in addition to insoluble alginate, from 40% to 90% of another polysaccharide, more preferably from 60% to 85% and most preferably from 70% to 80% of another polysaccharide which is most preferably carboxymethyl cellulose or pectin or a mixture thereof.
20 Polysaccharides suitable for use in fibres according the invention include carboxymethyl cellulose, carboxyethyl cellulose, other derivatives of cellulose, cellulose, pectin, hyaluronic acid and chitosan. Preferably the insoluble alginate is calcium alginate.

25 Preferably the fibres comprise from 10% to less than 50% by weight of the fibre of insoluble alginate, more preferably 10% to 49%, more preferably 15% to 40% and most preferably from 20% to 30% by weight of the fibre of water insoluble
30 alginate. Preferably the insoluble alginate is calcium alginate.

A particularly preferred embodiment of the absorbent, composite fibres of the invention comprise a matrix of 20%

5 to 30% of calcium alginate based on the weight of the fibre having dispersed therein from 55% to 60% of carboxymethyl cellulose and 15% to 20% of pectin based on the weight of the fibre.

10

Accordingly in another aspect the invention provides a method for making a composite, absorbent fibre comprising the following steps:

- 15 (i) adding sodium alginate and another polysaccharide to water to form a dope;
- (ii) forcing the dope through a spinneret to form fibres;
- (iii) treating the resulting fibres with a source of calcium ions to convert the alginate to calcium alginate and cross-link the alginate to the other polysaccharide;
- 20 (iv) drying the fibres.

The process enables composite fibres to be prepared which comprise large quantities of other polysaccharides and in particular, carboxymethyl cellulose, pectin or both. The fibres so produced are capable of being spun or otherwise mechanically processed. In addition the resulting fibres have a high tensile strength compared to alginate, carboxymethyl cellulose or pectin alone.

30 As used herein the term fibre means both relatively short, discrete, randomly oriented material (sometimes known as staple fibre) and yarns made therefrom (sometimes known as staple yarn) and relatively long, structured, continuous filament yarn. The fibres may have a staple length of 5mm

5 to 70 mm, more usually 20mm to 50 mm, favourably 25mm to 40 mm.

The fibres prepared according to the above described process may be dried using conventional methods, for
10 example, using acetone or hot air drying.

Alginates are produced by a variety of micro-organisms and marine algae which are the normal commercial source. The alginates being natural materials show considerable variety
15 but are characterised in being block copolymers, the individual monosaccharide units being arranged into groups as blocks of mannuronic (M) and guluronic (G) residues. In addition to the repeating blocks each polymer chain can contain a proportion of alternating M and G monosaccharide
20 units. The alginate may be obtained from any convenient source, for example L. Hyperborea or Ascophyllum Nodosum or those described in EP-A-0721355 to Bristol-Myers Squibb Company which are particularly preferred.

25 In a further embodiment of the invention the absorbent, composite fibres are employed in the manufacture of wound dressings. Accordingly the invention provides a wound dressing comprising an absorbent, composite fibre
30 comprising a matrix of between at least 10% and less than 50% of water insoluble alginate having dispersed therein at least 40% of another polysaccharide.

The wound dressings may be in the form of swabs, wound

5 pads, wadding ribbons, sponges, nets and bandages and may
be used as a primary or secondary dressing especially in
the treatment of leg ulcers. The wound dressings according
to the invention may benefit from an improved integrity
over that of dressings made from alginate, pectin or
10 carboxymethyl cellulose alone.

According to a further aspect of the invention there is
provided a wound dressing comprising a mixture of discrete
textile fibres and discrete absorbent, composite fibres
15 said absorbent, composite fibres comprising a matrix of at
least 10% of water insoluble alginate having dispersed
therein at least 40% of another polysaccharide. Such a
dressing may have the advantage that it is non-adherent to
wound tissue while being absorbent and relatively
20 inexpensive and the added advantage that it may be retained
on the wound for longer than conventional cotton gauze.
The absorbent, composite fibres according to the invention
incorporated in the wound dressing become moist and
slippery or gelatinous upon the uptake of wound exudate.
25 This reduces the tendency for the textile fibres to adhere
to the wound.

In general textile fibres absorb liquids by capillary
action and are not hygroscopic. This means that their
30 absorbencies as measured by the free swell absorbancy test
are low such as less than 1 gram of liquid per gram of
fibre. Suitable textile fibres can be natural or synthetic
depending on the end use of the dressing and method of
manufacture. Suitable textile fibres are for instance

5 described in PCT/GB95/00114. For example where the dressing is made from a non-woven mixture of discrete fibres the textile fibre is preferably one that can be fused at relatively low temperatures, for example polypropylene. The entire dressing can be heat fused to
10 give a dressing with sufficient tensile strength that it may be removed intact from the wound even though saturated with exudate. This avoids the need for the painstaking removal from the wound of parts of a dressing that has lost its integrity on exposure to exudate.

15

Where the dressing is made from a woven mixture of discrete fibres the textile yarn can be polyester, polypropylene or polyamide or any other suitable support yarn. We have surprisingly found that it is possible to knit fibres of
20 the invention in a knitting process where it is preferable for the textile yarn to form the pillar or chain stitches of the knit (the warp) and the composite fibre to form or be included in the the in-laid yarn of the knit. A particularly suitable knit of this type is a Raschel knit
25 as described in Textile Science by Kathryn Hatch, West Publishing Company 1993. If composite fibres are included in both the pillar and the in-laid yarn then the pillar yarn tends to break and shed fibres. If composite fibres are included only in the in-laid yarn then this tendency is
30 overcome and quite high machine knitting speeds can be achieved and a dressing of better integrity is produced.

According to a further aspect the invention provides a wound dressing as claimed in claims 11 to 14 wherein the

5 dressing is in the form of a warp knitted fabric comprising pillar yarn and in-laid yarn, the pillar yarn being substantially free of composite fibres.

Various optional ingredients can be included in the final
10 composition of the fibres such as preservatives and small amounts of pharmacologically active ingredients. For example an antibiotic or antimicrobial agent such as metronidazole, silver sulphadiazine, neomycin or penicillin and antiseptic agent such as povidone iodine, iodine and
15 antiinflammatory agent such as hydrocortisone or triamcinolone acteonide or a skin protective agent such as a zinc oxide can be included.

The invention is illustrated by the following examples:-

20

Example 1

Fibres according to the invention in the form of a continuous yarn were prepared as follows:

800ml of a 6% w/w dope was made by adding 28g of
25 carboxymethyl cellulose (ex Hercules), 12g of alginate (ex Kelco), and 8g of pectin (ex Aldrich Ltd) to 752g of deionised water. The mixture was stirred with a high speed mixer until the ingredients had dissolved and the dope allowed to stand overnight to degas.

30

The degassed dope was then poured into a pressure vessel connected to the dope pumping/filtering system of a spinning rig. The pressure vessel was pressurised to 2 to 3 atmospheres with compressed air and the pump, 60µm pore

5 size filter and associated pipe work purged to remove any
air bubbles. A 400 jet spinneret, previously
ultrasonically cleaned for 20 minutes, was connected to the
rig and the rig started. On exit from the spinneret, the
dope was fed into a spin bath of 2m length containing 30L
10 of 0.4 mol/dm³ of calcium chloride. The fibres so produced
were threaded over three sets of rollers of a first godet
and then over the rollers of a second godet. Propan-2-ol
was dripped onto the fibres at a rate sufficient to wet the
resulting yarn. The yarn was then passed into two baths,
15 the first contained 4L of propan-2-ol and the second
contained 2.5L of propan-2-ol. The propan-2-ol was
maintained at a concentration to dry the yarn. The yarn
was then passed through a set of pinch rollers that serve
to apply tension to yarn. The yarn was then wound onto
20 cones. The dope was supplied to the system at 6ml per
minute and a speed differential maintained between the
first and second godets resulted in a stretch of 60%. The
resulting yarn had a denier of 300 to 400.

25 Example 2

A knitted wound dressing according to the invention was
prepared comprising the yarn of example 1 and a crimped
polyester yarn. The dressing was knitted on a crochet
knitting machine (Model STP7 ex KOHLER) each needle of
30 which creates a chain of interlocked loops (pillar or clain
stitches). These form the warp threads of the dressing.
The warp threads are held together by weft threads. 45 warp
threads of stiches were knitted from 150 denier crimped
polyester yarn. These were held together by 44 threads of

5 the yarn of example 1 (in-laid yarn) to form a dressing.

Example 3

A non-woven wound dressing according to the invention was made by mixing 200g of the absorbent, composite fibres of example 1 cut into 5cm lengths and 200g of polypropylene staple fibre cut to 5cm lengths in a rag roller to randomise the fibre. The mixture of fibres was then carded and cross-lapped into a web of 100gsm basis weight. The web was then passed through heated callender rollers at 65°C and pressure. The resultant product was slit into discrete dressings 10cm by 10cm square.

Example 4

A staple yarn was made from the composite fibres of the invention in the following way. A mixture of the composite fibre (20kg) and polypropylene (20kg) (all 3 denier) was cut to a staple length of 40mm and converted into a lap of approximately 100gsm on a conventional short staple scutching line - a Truteschler Opening line. The line comprised a feed table, coarse fibre opener, volumetric feeder, fine opener and lap former.

The lap once formed was fed into a worsted type carding machine - a Thibau CA6 comprising a weigh pan hopper, fibre opening section and a main carding cylinder. The web of fibres formed was condensed into the form of a sliver with an average weight of 5 grammes per metre length.

The slivers were then attenuated on a conventional short-

5 staple draw frame - a Platts Globe Draw Frame - in which
rollers operated at differential surface speeds to
attenuate the multiple feed of slivers (6-8) into a uniform
single sliver of uniform weight and thickness
(approximately 3g per metre length).

10

The drawn sliver was converted into roving on a roving
frame which further attenuates the sliver. Twist was
inserted to add cohesion to the strand. The roving was
then spun on a ring spinning machine in which further
15 drafting took place and twist was inserted to form the
final yarn.

5

CLAIMS

1. An absorbent, composite fibre comprising a matrix of from at least 10% to less than 50% by weight of water insoluble alginate having dispersed therein at least 40% by weight of another polysaccharide.
2. An absorbent composite fibre as claimed in claim 1 wherein the water insoluble alginate is calcium alginate.
3. An absorbent composite fibre as claimed in claim 1 or claim 2 wherein the other polysaccharide is selected from the group comprising carboxymethyl cellulose, carboxyethyl cellulose, other derivatives of cellulose, cellulose, pectin, hyaluronic acid and chitosan.
4. An absorbent composite fibre as claimed any preceding claim wherein the fibres comprise from 40% to 90% by weight of another polysaccharide, preferably 60% to 85% by weight.
5. An absorbent composite fibre as claimed in any preceding claim wherein the fibres comprise from 70% to 80% by weight of another polysaccharide.
6. An absorbent, composite fibre as claimed in any preceding claim wherein the other polysaccharide is carboxymethylcellulose or pectin or a mixture thereof.
7. An absorbent, composite fibre as claimed in any preceding claim wherein the fibres comprise from 10% to 49%

5 by weight of the fibre of calcium alginate, preferably 30% to 40%.

8. An absorbent, composite fibre as claimed in any preceding claim wherein the fibres comprise from 20% to 30%
10 by weight of the fibre of calcium alginate.

9. A method for making a composite, absorbent fibre comprising the following steps:

- (i) adding sodium alginate and another polysaccharide to
15 water to form a dope;
(ii) forcing the dope through a spinneret to form fibres;
(iii) treating the resulting fibres with a source of ions to convert the alginate to water insoluble alginate and cross-link the alginate to the other polysaccharide;
20 (iv) drying the fibres.

10. A method as claimed in claim 8 wherein the source of ions in step (iii) is calcium ions.

25 11. A wound dressing comprising an absorbent, composite fibre comprising a matrix of from 10% to less than 50% of water insoluble alginate having dispersed therein at least 40% of another polysaccharide.

30 12. A wound dressing comprising a mixture of discrete textile fibres and discrete absorbent, composite fibres said absorbent, composite fibres comprising a matrix of from 10% to less than 50% of water insoluble alginate having dispersed therein at least 40% of another

5 polysaccharide.

13. A wound dressing as claimed in claim 12 comprising
from 50% by weight to 95% by weight of textile fibres and
5% by weight to 50% by weight of absorbent, composite
10 fibres.

14. A wound dressing as claimed in any claim 11 or claim
12 comprising from 75% to 90% by weight of textile fibres
and 10% to 25% by weight of absorbent, composite fibres.
15

15. A wound dressing as claimed in claims 11 to 14 wherein
the fibres are in the form of a woven fabric.

16. A wound dressing as claimed in claims 11 to 15 wherein
the fibres are in the form of a carded web.
20

17. Use of a wound dressing as claimed in claims 11 to 16
for the treatment of a wound by placing the dressing in
direct contact with the wound.
25

18. A wound dressing as claimed in claims 12 to 15 wherein
the dressing is in the form of a knitted fabric comprising
support yarn and in-laid yarn, the support yarn being
substantially free of composite fibres.
30

19. A wound dressing as claimed in claim 18 wherein the
fabric is a warp knitted fabric.

INTERNATIONAL SEARCH REPORT

Intern. Appl. No.
PCT/EP 97/01880

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 D01F9/04 D01F2/28 A61L15/28

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 D01F A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 96 10106 A (INNOVATIVE TECH LTD ;QIN YIMIN (GB); GILDING KEITH DENNIS (GB)) 4 April 1996 cited in the application see the whole document ---	1-19
A	DATABASE WPI Section Ch, Week 8814 Derwent Publications Ltd., London, GB; Class A32, AN 88-093952 XP002037006 & JP 63 042 917 A (AGENCY OF IND SCI & TECHNOLOGY) , 24 February 1988 see abstract --- -/-	1-19

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search

6 August 1997

Date of mailing of the international search report

19.08.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Tarrida Torrell, J

INTERNATIONAL SEARCH REPORT

Intern. Application No
PCT/EP 97/01880

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>DATABASE WPI Section Ch, Week 8705 Derwent Publications Ltd., London, GB; Class B04, AN 87-033299 XP002037007 & JP 61 289 886 A (AGENCY OF IND SCI & TECHNOLOGY) , 19 December 1986 see abstract</p> <p style="text-align: center;">---</p>	1-19
A	<p>WO 95 19795 A (SQUIBB BRISTOL MYERS CO ;LYDON MICHAEL JAMES (GB); QUEEN DOUGLAS () 27 July 1995 cited in the application</p> <p style="text-align: center;">-----</p>	

INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern. Application No

PCT/EP 97/01880

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9610106 A	04-04-96	AU 3530695 A	19-04-96
		EP 0783605 A	16-07-97
		GB 2307687 A	04-06-97

WO 9519795 A	27-07-95	AU 1667395 A	08-08-95
		CA 2179415 A	27-07-95
		EP 0740554 A	06-11-96
		FI 962916 A	19-07-96
		NO 962316 A	03-07-96

Form PCT/ISA/210 (patent family annex) (July 1992)

